

Trade name: **E-CTFE-GK**
 Date of printing: 04.02.2016

Revision: 19.09.2014

E-CTFE-GK

Data sheet update	19.09.2014
Moulding compound extruded	ECTFE-K,EGN,X.4C3.E.F.E.B
Extruded to moulding compound standard	ISO 12086-1
Density, g/cm ³ , DIN EN ISO 1183	1.68
Tensile modulus of elasticity, MPa, DIN EN ISO 527	1650
Yield stress, MPa, DIN EN ISO 527	31
Elongation at yield, % , DIN EN ISO 527	4
Impact strength, KJ/m ² , DIN EN ISO 179	without break
Notched impact strength, kJ/m ² , DIN EN ISO 179	100
Ball indentation hardness, MPa, DIN EN ISO 2039-1	56
Shore hardness D (15 s), DIN EN ISO 868	74
Mean coefficient of linear thermal expansion, K ⁻¹ , ISO 11359-2	1,0 × 10 ⁻⁴
Vicat B, °C , DIN EN ISO 306	118
Fire behaviour DIN 4102	DIN 4102 B1 low flammability (self-assessment without test certificate)
Surface resistivity, Ohm , DIN IEC 60093	10 ¹⁴
Temperature range, °C	-40 to +150

The data presented in this section are to be seen as a guide and may vary depending on the processing method and test specimen used. In general, the figures are averages of tests performed on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured by means of pressing, testing is generally performed on sheets with a thickness of 20 mm. Deviations may be possible if sheets are not available in these specific thicknesses. In the case of backed sheets, all technical specifications relate to the non-backed base sheets. Please note that this information is not necessarily applicable to products that have undergone downstream processing. The suitability of a material for a specific area of application must be checked by the processor or end user. All technical specifications are provided only as a guide for planning purposes. They do not constitute a guarantee of specific properties or qualities. For further information, please contact our Technical Service Centre at tsc@simona.de.