

Trade name: **PE-HD natural**
 Date of printing: 03.02.2016

Revision: 28.09.2015

PE-HD natural	
Data sheet update	28.09.2015
Moulding compound extruded	PE,EN,45 T 003/6
Extruded to moulding compound standard	DIN EN ISO 17855-1
Moulding compound pressed	PE,QN,45 T 003/6
Pressed to moulding compound standard	DIN EN ISO 1872, Teil 1
Density, g/cm ³ , DIN EN ISO 1183	0.95
Tensile modulus of elasticity, MPa, DIN EN ISO 527	1100
Yield stress, MPa, DIN EN ISO 527	23
Elongation at yield, % , DIN EN ISO 527	9
Impact strength, KJ/m ² , DIN EN ISO 179	without break
Notched impact strength, kJ/m ² , DIN EN ISO 179	21
Ball indentation hardness, MPa, DIN EN ISO 2039-1	43
Shore hardness D (15 s), DIN EN ISO 868	64
Mean coefficient of linear thermal expansion, K ⁻¹ , ISO 11359-2	1,8 × 10 ⁻⁴
Fire behaviour DIN 4102	DIN 4102 B2 normal flammability (self-assessment without test certificate)
Dielectric strength, kV/mm , DIN IEC 60243-1	50
Surface resistivity, Ohm , DIN IEC 60093	10 ¹⁴
Temperature range, °C	-50 to +80
Physiological safety in accordance with EU	yes
Physiological safety in accordance with FDA	yes

The data presented in this section are to be seen as a guide and may vary depending on the processing method and test specimen used. In general, the figures are averages of tests performed on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured by means of pressing, testing is generally performed on sheets with a thickness of 20 mm. Deviations may be possible if sheets are not available in these specific thicknesses. In the case of backed sheets, all technical specifications relate to the non-backed base sheets. Please note that this information is not necessarily applicable to products that have undergone downstream processing. The suitability of a material for a specific area of

PE-HD natural

application must be checked by the processor or end user. All technical specifications are provided only as a guide for planning purposes. They do not constitute a guarantee of specific properties or qualities. For further information, please contact our Technical Service Centre at tsc@simona.de.