

Trade name: **PP-DWU-B**  
 Date of printing: 02.12.2014

Revision: 19.09.2014

<b>PP-DWU-B</b>	
Data sheet update	19.09.2014
Moulding compound extruded	PP-H,ECH,16-09-003
Extruded to moulding compound standard	DIN EN ISO 1873, Teil 1
Moulding compound pressed	PP-H,QCH,16-09-003
Pressed to moulding compound standard	DIN EN ISO 1873, Teil 1
Density, g/cm <sup>3</sup> , DIN EN ISO 1183	0.915
Yield stress, MPa, DIN EN ISO 527	32
Elongation at yield, % , DIN EN ISO 527	8
Tensile modulus of elasticity, MPa, DIN EN ISO 527	1400
Impact strength, KJ/m <sup>2</sup> , DIN EN ISO 179	without break
Notched impact strength, kJ/m <sup>2</sup> , DIN EN ISO 179	7
Ball indentation hardness, MPa, DIN EN ISO 2039-1	70
Shore hardness D (15 s), DIN EN ISO 868	72
Mean coefficient of linear thermal expansion, K <sup>-1</sup> , ISO 11359-2	1,6 × 10 <sup>-4</sup>
Fire behaviour DIN 4102	B2 normal flammability (self-assessment without test certificate)
Dielectric strength, kV/mm , DIN IEC 60243-1	52
Surface resistivity, Ohm , DIN IEC 60093	10 <sup>14</sup>
Temperature range, °C	0 to +100
Physiological safety in accordance with BfR (German Federal Institute for risk valuation)	yes

The data presented in this section are to be seen as a guide and may vary depending on the processing method and test specimen used. In general, the figures are averages of tests performed on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured by means of pressing, testing is generally performed on sheets with a thickness of 20 mm. Deviations may be possible if sheets are not available in these specific thicknesses. In the case of backed sheets, all technical specifications relate to the non-backed base sheets. Please note that this information is not necessarily applicable to products that have undergone downstream processing. The suitability of a material for a specific area of application must be checked by the processor or end user. All technical specifications are provided only as a guide for

---

**PP-DWU-B**

planning purposes. They do not constitute a guarantee of specific properties or qualities. For further information, please contact our Technical Service Centre at [tsc@simona.de](mailto:tsc@simona.de).