

Trade name: **PVC-C CORZAN FM 4910 G2**

Revision: 18.03.2015

Date of printing: 04.02.2016

PVC-C CORZAN FM 4910 G2

Data sheet update	18.03.2015
Moulding compound extruded	PVC-C, EDP, 094-25-T23
Extruded to moulding compound standard	DIN EN ISO 1163, Teil 1
Density, g/cm ³ , DIN EN ISO 1183	1.56
Tensile modulus of elasticity, MPa, DIN EN ISO 527	2500
Yield stress, MPa, DIN EN ISO 527	53
Elongation at yield, % , DIN EN ISO 527	4
Impact strength, KJ/m ² , DIN EN ISO 179	without break
Notched impact strength, kJ/m ² , DIN EN ISO 179	12
Shore hardness D (15 s), DIN EN ISO 868	82
Mean coefficient of linear thermal expansion, K ⁻¹ , ISO 11359-2	0,7 x 10 ⁻⁴
Vicat B, °C , DIN EN ISO 306	95
Fire behaviour DIN 4102	DIN 4102 B1 low flammability (self-assessment without test certificate)
Fire behaviour FM 4910	FM 4910 low flammability
Surface resistivity, Ohm , DIN IEC 60093	10 ¹⁵
Temperature range, °C	-40 to +85
Physiological safety in accordance with BfR (German Federal Institute for risk valuation)	no
Physiological safety in accordance with EU	no
Physiological safety in accordance with FDA	no

The data presented in this section are to be seen as a guide and may vary depending on the processing method and test specimen used. In general, the figures are averages of tests performed on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured by means of pressing, testing is generally performed on sheets with a thickness of 20 mm. Deviations may be possible if sheets are not available in these specific thicknesses. In the case of backed sheets, all technical specifications relate to the non-backed base sheets. Please note that this information is not necessarily applicable to products that have undergone downstream processing. The suitability of a material for a specific area of application must be checked by the processor or end user. All technical specifications are provided only as a guide for

PVC-C CORZAN FM 4910 G2

planning purposes. They do not constitute a guarantee of specific properties or qualities. For further information, please contact our Technical Service Centre at tsc@simona.de.