

Garantie

PLEXIGLAS® Optical

hard coated (HC)

Valid from : 08 / 2013

Guarantee statements

We guarantee the following properties for the above product according to the conditions of the guarantee statement:

Yellowness (according to DIN 6167)

Yellowness index	Climate zone: temperate
on delivery	max. 1
after 5 years	max. 4

Light transmission (according to DIN 5036)

Transmittance	Climate zone: temperate
on delivery	min. 90%
after 5 years	min. 88%

Haze (according to ASTM D 1003)

Haze	Climate zone: temperate
on delivery	max. 1%
After 5 years	max. 3%

Adhesion of coating (according to DIN EN ISO 2409)

Adhesion	Climate zone: temperate
on delivery	GT 0
after 5 years	GT 0

Combustion behaviour

Colourless PLEXIGLAS® Optical hard coated burns nearly smoke free and produces no acutely toxic flue gases. PLEXIGLAS® Optical is considered harmless in this respect.

Guarantee: PLEXIGLAS® Optical hard coated (HC)

Explanations

We guarantee the following properties for the above product for the temperate climate zone

Yellowness

Colourless, transparent PLEXIGLAS® Optical hard coated has a yellowing value of 0 to 1 when new. The mentioned delta of the yellowing value refers to the temperate climate zone (see picture below). The yellowing value is measured as per DIN 6167 on cleaned and polished specimens conditioned in a standardized climate at 23 ° C / 50 % RH until equilibrium is reached.


Light transmission

Colourless PLEXIGLAS® Optical hard coated has a light transmission when new of up to 92% depending on product type and design. The transmission factor t_{D65} is measured as per DIN 5036 on cleaned and polished specimens with a thickness of 1mm, conditioned in a standardized climate at 23 ° C / 50 % RH until equilibrium is reached.

Combustion behaviour

Light absorption by smoke is measured acc. to DIN 4101-1 Annex B. PLEXIGLAS® Optical hard coated burn nearly smoke-free. The acute toxicity of flue gases is measured as per DIN 53436 and is defined as harmless and not toxic. The material is according to DIN EN 13501-1 normal flammable and is classified to class E - not emitting burning droplets. The properties guaranteed for PLEXIGLAS® apply to all climate zones.

Climate zones



Guarantee: PLEXIGLAS® Optical hard coated (HC)

Terms of guarantee

Terms of guarantee, exclusions

All guarantee values shall be determined using cleaned specimens. The products must have been stored, transported, processed, installed and used in accordance with the requirements of the subject materials. They must not have been thermally moulded or exposed to detrimental effects of harmful chemicals. For information on proper use, care and deployment of our products go to <http://www.plexiglas.net> on the internet and see the relevant print publications.

Duration of guarantee

This guarantee begins with the day of delivery to the end-user and expires upon deinstallation of the first application, intentional or wilful destruction, or after the guaranteed time (5 years after date of purchase). The shortest of the stated time spans applies in each case. Any guarantee claims shall exclusively be determined and governed by the version of this guarantee statement valid on the date of purchase of the material in questions. The applicable version in each case is found at <http://www.plexiglas.net>

In case of guarantee claim

Any rights or claims raised hereunder shall be subject to the following,

- The user must present us a bill from the seller showing the name and address of the user, date of purchase, full product type / name and the product quantity so purchased.
- The guarantee claim must be submitted to us, during the term of this guarantee, in writing within 30 days.
- We ourselves must without delay be permitted to inspect the defect and its potential cause on site, or to have another party do so on our behalf.

Claims exclusively available hereunder

In case all terms and other conditions hereof are fulfilled such that the user has a valid claim hereunder we will replace the defective PLEXIGLAS® product ex works. If equivalent replacement material is no longer manufactured by us or can no longer be supplied, the user will receive a refund of the original purchase price. No other or further rights or claims on any kind shall be available hereunder.

Consumer rights, applicable law & jurisdiction

This guarantee does not affect or restrict any rights or claims specifically available to consumers under applicable law. This guarantee shall exclusively be governed by and construed under the laws of Germany, as applicable on the date of purchase of the goods in questions, without giving effect to conflict of laws principles. The exclusive place of jurisdiction for any rights or claims from this guarantee shall be Darmstadt, Germany.

® = registered trademark PLEXIGLAS is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany.

Certified to DIN EN ISO 9001 (Quality) and DIN ES ISO 14001 (Environment)

Evonik is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, also with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could be used.

Evonik Performance Materials GmbH

Acrylic Polymers

Kirschenallee, 64293 Darmstadt, Germany

info@plexiglas.de www.plexiglas.de www.evonik.de

Ref.-No. 111-105 July 2015